

Keratherm Thermal Grease



Ceramic-filled single component silicone with a high thermal conductivity.

The non-crosslinked thermal compounds do not dry out.

APPLICATIONS

- Notebooks
- Desktop CPU's
- Heat Pipes

DISCLAIMER: Purchaser shall be solely responsible for determining the adequacy of the product for any and all uses which the purchaser shall apply the product, and the application of the product by the purchaser shall not be subject to any implied warranty of fitness for that purpose.

Properties	symbol	unit	KP 96
Color			Dark white
Consistency			soft/paste
Thermal Properties			
Thermal Resistance	R_{th}	K/W	0.038
Thermal Impedance	R_{ti}	$^{\circ}\text{Cmm}^2/\text{W}$ Kin^2/W	11 0.017
Thermal Conductivity	λ	W/mK	2.4
Electrical Properties			
Dielectric Breakdown	$E_{d;ac}$	KV/mm	conductive
Mechanical Properties			
Coating Thickness		mm	0.035
Viscosity		Pas	25 - 35
Density		g/cm^3	2.6
Application Temperature		$^{\circ}\text{C}$	-60 to +150
Long Term Stability (1000h / 85$^{\circ}\text{C}$ / 85% relative humidity)			
Thermal Resistance	R_{th}	K/W	0.038
Total Mass Loss (TML)		Ma.-%	≤ 1.4

The silicone components do not leak out of the compound. Special storage of KP 96/97/98 is not required; therefore they can be stored under normal climate conditions for up to 12 months. If any separation of the filler materials becomes evident, KP 96/97/98 must be mixed thoroughly before use.

KP 96, KP 97 and KP 98

Comparison of the thermal resistance of different pastes in dependence on the contact pressure

